



J·DRAIN[®]

CD 60 Series Chimney Drain Systems



J·DRAIN[®] CD 60 Series Chimney Drain Systems

Product Description:

Chimney Drains are available in 12", 18", or 24" wide strips of .4" profile dimple drainage core bonded to a layer of filter fabric. Their purpose is to draw the ground water which migrates through the soil adjacent to the wall and quickly convey the water down to the base collection system (**J·DRAIN SWD**), providing hydrostatic relief. Often dense compacted soil layers form between the base part and the top of the backfill and water collecting against the wall has difficulty finding its way to the base collection system. Chimneys add very little to the overall cost of the system, but greatly enhance the effectiveness of the drainage system. Available in 12, 18, & 24" widths. Also available with AASHTO approved fabric.

Applications:

Popular applications for chimneys are **retaining** and **lagging** walls or other vertical applications where full wall coverage is not feasible. Often times in these applications, chimney drains provide a practical alternative to accommodate for protrusions in the wall surface, i.e. tie backs & soil nails. Chimney drains may also be used as a cost effective alternative when full wall coverage is not cost effective and not required.

J·DRAIN CD 60

J·DRAIN CD 64

J·DRAIN CD 66

info@j-drain.com

www.j-drain.com

JDR Enterprises, Inc.

292 S. Main St., Suite 200 Alpharetta, GA 30009
(800) 843-7569 (770) 442-1461 Fax: (770) 664-7951



J·DRAIN[®]

CD 60 Series Chimney Drain Systems

Physical Properties

Property	Test Method	UOM	CD 60	CD 64	CD 66
FABRIC					
Material			Non woven PP	Non woven PP	Non woven PP
AASHTO M 288	Survivability		-	<i>Class 3</i>	<i>Class 2</i>
Grab Tensile Strength	ASTM D 4632	lbs	100	120	160
		N	450	534	712
Apparent Opening Size	ASTM D 4751	U.S. Sieve	70	70	70
		mm	0.212	0.212	0.212
Flow Rate	ASTM D 4491	gal/min/ft ²	140	135	110
		l/min/m ²	5704	5500	4481
Puncture Strength	ASTM D 6241	lbs	250	310	410
		N	1110	1380	1825
Permittivity	ASTM D 4491	sec ⁻¹	2.0	1.7	1.5
Grab Tensile Elongation	ASTM D 4632	%	60	50	50
UV Resistance	ASTM D 4355	% (@ 500 hrs)	70	70	70
CORE					
Thickness	ASTM D 1777	inch	0.4	0.4	0.4
		mm	10.16	10.16	10.16
Compression	ASTM D 1621	psf	21,000	21,000	21,000
		kNm ²	1005	1005	1005
Flow Rate Hydraulic Gradient = 1 @3,600 psf	ASTM D 4716	gal/min/ft	23	23	23
		l/min/m	286	286	286
ROLL SIZE					
Roll Width		inch	12, 18, & 24		
		cm	30.5, 45.7, & 61		
Roll Length		feet	150 & 300		
		meters	45.72 & 91.44		

Specialty roll widths and fabrics require additional lead time and minimum quantity orders.

The information contained herein is believed by JDR Enterprises, Inc. to be accurate and is offered solely for the customer's consideration, investigation and verification. Determination of suitability for use is the responsibility of the user. JDR's Limited Warranty, & Disclaimer along with Standard Terms & Conditions apply. See www.j-drain.com for more info. Limitations: J-DRain is resistant to chemicals in normal soil environments. However, some reagents may affect the performance of J-DRain. A JDR representative should be contacted for further information to determine the suitability of use of J-DRain in unusual soil environments. J-DRain should be limited to its exposure to ultra-violet sunlight. J-DRain should be backfilled or covered within seven days of installation. Disclaimer: All information, drawings and specifications are based on the latest published information at the time of printing. JDR reserves the right to make changes due to manufacturing improvements and engineering at any time. All physical properties are minimum average roll values (MARV). Standard variations of 10% in mechanical properties and 15% in hydraulic properties are normal.

info@j-drain.com

www.j-drain.com

JDR Enterprises, Inc.

292 S. Main St., Suite 200 Alpharetta, GA 30009
(800) 843-7569 (770) 442-1461 Fax: (770) 664-7951